



Jiaxing Green Shield New Materials Co.,
Ltd
Add: No.365 West Qianjiang Road, Haining,
Zhejiang, China

20 OZ(680gsm) PVC Laminated Blockout Fabric
Anti-UV, Color fastness, NFPA701 FIRE PROOF

Properties	Units	Test method	Average value
Base Thread Density	Denier	DIN53350	1000*1000D
Base Fabric Density	Thread/inch	DIN53351	9*9
Finished Fabric Weight	Gram/m2	DIN53352	680
Base Fabric Weight	Gram/m2	DIN53352	88
Thickness - finished product	um	DIN53352	50
Break Strength Warp	N/5cm	GB/T1040	1200
Break Strength Weft	N/5cm	GB/T1040	1000
Tear Strength Warp	N/5cm	DIN 53363	250
Tear Strength Weft	N/5cm	DIN 53363	200
Adhension	N/5cm	DIN 53357	120
Temperature range	°C	DIN 53368	-40 ~ +70
Flame Retardant	NFPA701 , no fire drops		